

BIOCLEAN-D HOOD

Sterile Longer Length
S-BDHD-L

About

The single use BioClean-D Sterile Hood has a three-piece design to ensure a perfect fit. Made from antistatic lightweight CleanTough material for comfort, the hood features an extra-long yoke for maximum coverage when worn in conjunction with a coverall with collar, and features an elasticated face-opening with reinforced edges to avoid contamination entering the controlled environment.

EXTRA-LONG YOKE

THREE PIECE DESIGN

ANTISTATIC

Specifications

MATERIAL:

Antistatic BioClean-D CleanTough white material

COLOUR:

White

CONSTRUCTION:

Bound seams with single needle stitching

CLASSIFICATION:

PPE Cat 3 Type PB [6]

CHARACTERISTICS:

Antistatic to EN1149-5* & low particulating

COMPATIBILITY:

ISO Class 4 & EU GMP Grade A

STERILIZATION:

Gamma irradiation

Features

- Extra-long yoke for maximum coverage
- Lightweight low-linting CleanTough material
- Excellent ESD properties
- PPE Cat 3 Type PB [6]



Quality Standards

- Manufactured in a facility holding ISO 9001:2008 and 89/686/EEC Article 11b certifications
- Conforms to Category 3 - Complex Design Personal Protective Equipment PPE Directive 89/686/EEC
- Tested against standard EN ISO 13034 protective clothing against liquid chemicals (Type PB[6])
- Tested against standard EN ISO 14325 protective clothing against chemicals
- Tested against standards: EN 1149-5*, protective clothing - electrostatic properties; EN 530, Abrasion resistance; EN 7854, Flex cracking resistance; EN 6530, Resistance to penetration by liquids; EN 13934-1, Tensile strength; EN 9073-4, Trapezoidal tear resistance; EN 863, Puncture resistance; and EN 13935-2, Seam strength.
- Tested against permeation standard ASTM F739-12
- Processed in an NEBB certified ISO Class 4 environment
- Sterilized in accordance with ISO 11137-1:2006

Sterilization

Method: Gamma irradiation
 Minimum Dose: 25kGy
 Sterility Assurance Level: 10^{-6}

Shelf Life & Storage

Three (3) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

Performance Test Results – BioClean-D CleanTough White Material

TEST	RESULT		PERFORMANCE CLASS (EN 14325)
Abrasion Resistance	10 to 100 cycles		1
Flex Cracking Resistance	5,000 to 15,000 cycles		3
Trapezoidal Tear Resistance	CD 29.3 N		2
Trapezoidal Tear Resistance	MD 55.5 N		3
Tensile Strength	MD 97 N		2
Tensile Strength	CD 48 N		1
Puncture Resistance	8 N		1
Repellence to Liquids	30% H ₂ SO ₄	96.3%	3
	10% NaOH	97.6%	3
	O-Xylene	95.7%	3
	Butan-1-ol	96.6%	3
Penetration by Liquids	30% H ₂ SO ₄	0%	3
	10% NaOH	0%	3
	O-Xylene	0%	3
	Butan-1-ol	0%	3
Seam Strength	70 N		2
Electrostatic Charge Half Decay Time, t_{50} (secs)	0.07		Pass

¹Seam not destroyed.

Particle Shedding Test Results

TEST	RESULT	CATEGORY (IEST-RP-CC003.3)
Particle Shedding (Helmke Drum Test)	<260	Category I

BioClean-D™ CleanTough White Material - ASTM F739-12 Test Method Results

Mean Breakthrough Time (MBT), Minutes

Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 µg/cm²/min

CISPLATIN	CARMUSTINE	CYCLO- PHOSPHA- MIDE	DOXO- RUBICIN HYDRO- CHLORIDE	5- FLURO- URACIL	METHO- TREXATE	ETOPOSIDE	PACLITAXEL	THIOTEPA
>240	<6	217 (275,162,215)	>240	>240	>240	>240	<10	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

TO ORDER

Re-Order	Chest	Height	Size
S-BDHD-L	N/A	N/A	Universal

Packing

One piece per sealed inner PE bag; 20 inner bags per sealed outer PE bag; six outer bags per lined carton (120 pieces)

*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment

For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd

Minton Enterprise Park
Oaks Drive
Newmarket, Suffolk
CB8 7YY
United Kingdom

S-BDHD-L/1809/PDS9



Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of disposable garments for a specific application.

**Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and TM are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2018 Ansell Limited. All Rights Reserved.